

**REV. 05** 26/08/2024

PRODUCT DESCRIPTION

Xtreme LONG TRUCK 15W-40 PLUS is a premium quality multi-grade lubricant designed for diesel engine, that helps to extend engine life in the toughest on and off-road applications, while delivering outstanding performance in modern high-output, low-emission engines, including those with exhaust gas recirculation (EGR) and after-treatment systems with diesel particulate filters (DPF) and diesel oxidation catalysts (DOC).

Xtreme LONG TRUCK 15W-40 PLUS gives the following main benefits,

- High control blocking of a poisoning of exhaust after-treatment devices, •
- Outstanding resistance to corrosive and abrasive wear to maximize engine life,
- Excellent thermal and oxidation stability that increases fuel economy.
- High wear protection that increases efficiency and allows extended service intervals,
- Exceptional alkaline reserve (TBN),
- Good shear strength and viscosity stability,
- Outstanding low temperature pumpability,
- High compatibility with the seals of the post-treatment system (DPF and DOC).

## Xtreme LONG TRUCK 15W-40 PLUS is recommended in a wide range of heavy-duty **APPLICATIONS** applications and environmental conditions typical of road transport, mining / quarrying, shipbuilding and agriculture.

Xtreme LONG TRUCK 15W-40 PLUS meets the requirements of leading European and American engine manufacturers for applications requiring low emissions.

	API SN/CK-4
PERFORMANCE	
LEVELS AND	MB 228.31
APPROVALS	MAN M3775 a

CEA E7/E11 B 228.31 AN M3775 approval VOLVO VDS 4.5 approval RENAULT RLD-3 approval **RENAULT RLD-4** MACK EOS-4.5 approval

ALLISON TES 439 MTU TYPE 2.1 CATERPILLAR ECF-3 DEUTZ DQC III-18LA DETROIT DIESEL DFS 93K222 CUMMINS CES 20086 JASO DH2 FORD 171-F1

TYPICAL	Xtreme LONG TRUCK 15W-40 PLUS	TESTING PROCEDURE	TYPICAL VALUES
CHARACTERISTICS	SAE grade	-	15W-40
Ι	Density@15, kg/m³	ASTM D 1298	≥860
	Kinematic viscosity @100°C, cSt	ASTM D 445	12,3-16,5
	Viscosity index	ASTM D 2270	≥130
	Pour point, °C	ASTM D 97	≤-27
	Flash point, °C	ASTM D 92	≥220
	TBN, mg KOH/g	ASTM D 2896	≥ 9,0
	Sulfated ash, %w	ASTM D 874	≤ 1,0

INFORMATION ON THIS TDS HAS TO BE CONSIDERED UPDATED AT THE DATE OF THE DRAFING, HOWEVER VARIATIONS ON THE FORMULATION OR CHANGES ON THE PERFORMANCE OF THE PROCUCT LATER OCCURRED CAN INFLUENCE THE ACCURACY, IN ANY CASE THE ABOVE INFORMATION IS INDICATIVE, AND IT DOESN'T CONSTITUTE PERFORMING LEVEL OF SALE.